



2.3 mil TC White Polypropylene ** B-122TMF ** 40# liner

Item#: 0041892

	TRIMLESS PROGRAMS		
Dist. Ctr	Length	Min. Width	Core
- Troy, Ohio	2.5 K	3"	3"
Troy, Ohio	5 K	3"	3"
Troy, Ohio	10 K	4"	3"
New York	2.5 K	3"	3"
New York	5 K	3"	3"
New York	10 K	4"	3"
Atlanta	2.5 K	3"	3"
Atlanta	5 K	3"	3"
Atlanta	10 K	4"	3"
Chicago	2.5 K	3"	3"
Chicago	5 K	3"	3"
Chicago	10 K	4"	3"
Los Angeles	2.5 K	3"	3"
Los Angeles	5 K	3"	3"
Los Angeles	10 K	4"	3"

Facestock: 2.3 mil TC White Polypropylene

A glossy white, biaxially-oriented polypropylene designed with a unique top coating to be compatible with water-based and solvent-based inks.

Typical Value

Basis Weight:

Caliper:

Tensile MD/CD:

Elongation @ Break MD/TD:

Opacity:

39#/3300 ft

2.3mils

26,800 / 22,500PSI

80 / 100%

80%

Adhesive: **B-122**TM**F** A clear all temperature acrylic adhesive featuring excellent adhesion to a variety

of surfaces with film facestocks. It covers a broad temperature range and has excellent converting characteristics on press. The high initial tack of B-122F to low surface energy polyolefins makes it an ideal for blow on applications

Typical Value

Coat Weight:

13#/3300 ft²

Coat Weight:

19.24 grams/m²

Caliper:

.6 mils

Adhesion to Stainless Steel, oz. (90° Peel): 24





Loop Tack, oz.:	47
Service Temperature:	-65 to 200 °F
Minimum Application Temperature:	-10 °F
Shear (1000g):	75 minutes

Release Liner:40# liner	A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.	
	Typical Value	
Basis Weight:	41 #/3000 ft ²	
Caliper:	2.5 mils	
Tensile MD/CD:	34 / 21 #/inch	
Tear MD/CD:	34 / 36 grams	
Opacity:	69 max%	

Total Product Caliper: 5.4mils
Product Basis Weight Per MMSI: 204.42#
Shelf Life: 12month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.