



Let Us Label You

2.0 mil TC Gloss White Polyester ** B-122™F ** 40# liner

Item#: 0042147

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	2.5 K	3"	3"
Troy, Ohio	5 K	3"	3"
Troy, Ohio	10 K	4"	3"
Atlanta	2.5 K	3"	3"
Atlanta	5 K	3"	3"
Atlanta	10 K	4"	3"
Los Angeles	2.5 K	3"	3"
Los Angeles	5 K	3"	3"
Los Angeles	10 K	4"	3"

Facestock: 2.0 mil TC Gloss White Polyester

A top-coated, glossy white polyester facesheet offering high heat, tear, abrasion, solvent, and water resistance. It features excellent printability with conventional print methods, including thermal transfer when paired with the appropriate ribbon.

Basis Weight:

Typical Value

51#/3300 ft

Caliper:

2.0mils

Tensile MD/CD:

21,300 / 26,400PSI

Elongation @ Break MD/TD:

130 / 70%

Gloss:

98 / N/A%

Adhesive: B-122™F

A clear all temperature acrylic adhesive featuring excellent adhesion to a variety of surfaces with film facestocks. It covers a broad temperature range and has excellent converting characteristics on press. The high initial tack of B-122F to low surface energy polyolefins makes it an ideal for blow on applications

Typical Value

Coat Weight:

13#/3300 ft²

Coat Weight:

19.24 grams/m²

Caliper:

.6 mils

Adhesion to Stainless Steel, oz. (90° Peel):

24

Loop Tack, oz.:

47

Service Temperature:

-65 to 200 °F

Minimum Application Temperature:

-10 °F

Shear (1000g):

75 minutes



A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

Typical Value

Basis Weight:	41 #/3000 ft ²
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

Total Product Caliper: 5.1mils

Product Basis Weight Per MMSI: 229.68#

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.