





ScanThermTM NTC ** A-BC-20TM ** 40# liner

Item#	!: 0	045	63	1

		TRIMLESS PROGRAMS			
NAMES AND ADDRESS OF THE PARTY	Dist. Ctr	Length	Min. Width	Core	
******	Troy, Ohio	2.5 K	3"	3"	
-	Troy, Ohio	5 K	3"	3"	
	Troy, Ohio	10 K	4"	3"	

Facestock: **ScanTherm**TM **NTC** A direct thermal facestock designed for short-duration labeling.

As the sheet does not have a grease resistant top coating, it is not suitable for applications requiring water or chemical resistance

(solvents, oils, fats, or similar substances).

Typical Value

 Basis Weight:
 51#/3300 ft

 Caliper:
 3.3mils

 Tensile MD/CD:
 35 / 16

 Gloss:
 9%

Tear MD/CD: 43 / 44 grams

Opacity: 92%
Sheffield Smoothness: 25 SFU
Parker Print: 1.5 microns
Brightness: 87%

Adhesive: **A-BC-20**TM A-BC-20 is a light coat weight of BC-20 cold temperature permanent. It is a

hot melt, rubber based pressure adhesive featuring excellent adhesion to a variety of packaging materials and other substrates over a wide temperature range. In field processing, A-BC-20 standard constructions have displayed

excellent die cutting and stripping characteristics.

Typical Value

Coat Weight: $12\#/3300 \text{ ft}^2$ Coat Weight: 17.76 grams/m^2

Caliper: .5 mils Adhesion to Stainless Steel, oz. (90° Peel): 29 oz Loop Tack, oz.: 52 oz

Service Temperature: -50 to 145 °F

Minimum Application Temperature: 10 °F Shear (1000g): 58 minutes





Release Liner:40# liner	A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.		
	Typical Value		
Basis Weight:	41 #/3000 ft ²		
Caliper:	2.5 mils		
Tensile MD/CD:	34 / 21 #/inch		
Tear MD/CD:	34 / 36 grams		
Opacity:	69 max%		
Total Product Caliper: 6.3 mils Product Basis Weight Per MMSI: 227.58; Shelf Life: 12 month(s) when stored at 72° F		For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.	
Name of the production of the state of the s			