

Fasson® 2.6 Mil White BOPP TC/S2001/40#BG**Spec# 76835****Facestock:**

Fasson® 2.6 Mil White BOPP is a topcoated white biaxially oriented polypropylene film for rigid containers where durability is needed.

Basis Weight:	n/a
Caliper:	0.0026 inches ± 10%
Tensile:	MD 12,600 psi CD 22,200 psi
Tear:	n/a
Stiffness:	MD 21 mg (target)

Adhesive:

Fasson® S2001 is a clear permanent adhesive designed for prime film labeling where exceptional optical clarity is required. Suited to clear squeezable and clear facestock applications, S2001 provides short-term repositionability, and good ultimate adhesion to a wide variety of substrates. Meets the requirements of FDA 21 CFR 175.105 for indirect food contact.

Type:	Emulsion Acrylic
Minimum Application Temperature:	+25° F
Service Temperature Range:	-40° F to +200° F subject to facestock limitations

Typical Performance Data: 2 Mil Clear Polyester Facestock at room temperature on standard lab panels

Stainless Steel

Loop Tack:	2.5 lbs
Peel Adhesion:	2.2 lbs

Aluminum

Loop Tack:	N/A
Peel Adhesion:	2.8 lbs

Flame Treated Polypropylene

Loop Tack:	N/A
Peel Adhesion:	2.3 lbs

Flame Treated HDPE

Loop Tack:	N/A
Peel Adhesion:	1.4 lbs

Glass

Loop Tack:	N/A
Peel Adhesion:	2.4 lbs

1/25/2020

Standard Product Data Sheet - #76835

Liner:

Fasson® 40#BG is a bleached glassine white liner with excellent roll label converting properties. Designed for low- to medium-speed dispensing applications. Not recommended for sheeted applications. Features good back printability.

Basis Weight:	40# per ream $\pm 10\%$ (500 sheets 24" x 36")
Caliper:	0.0023 inches $\pm 10\%$
Tensile:	MD 36# per inch width CD 19# per inch width
Tear:	MD 36 grams CD 39 grams

Total Construction Caliper (approximate): 0.0057 inches $\pm 10\%$

Optimal Storage Conditions

Unless otherwise specified in this document, ideally store at 72F and 50% RH

Statement of Practical Use

All materials, sales and contracts for sale of Avery Dennison products are sold with the express requirement and understanding that the customer is solely and exclusively responsible for testing and for ensuring the products are fit for the customer's purposes or an end-user's purposes. All express or implied warranties of merchantability and fitness for particular use are disclaimed.

Warranty

All sales and contracts for sale are expressly conditioned on the buyer's assent to Avery Dennison's terms and conditions found on its website at label.averydennison.com/products. Avery Dennison hereby objects to any term, different from or additional to Avery Dennison's terms, contained in any buyer communication in any form, unless agreed to in a writing signed by an officer of Avery Dennison.

label.averydennison.com



Label and Packaging Materials-North America

8080 Norton Parkway
Mentor, OH 44060
800-944-8511

