



Let Us Label You

Fasson® 2.6 Mil White BOPP TC/S692N/40#BG

Spec# 76910 - EXACT™ Splice-Free

Facestock:

Fasson® 2.6 Mil White BOPP is a topcoated white biaxially oriented polypropylene film for rigid containers where durability is needed.

Basis Weight:	n/a
Caliper:	0.0026 inches ± 10%
Tensile:	MD 12,600 psi CD 22,200 psi
Tear:	n/a
Stiffness:	MD 21 mg (target)

Adhesive:

Fasson® S692N is a clear general purpose permanent acrylic adhesive. It exhibits a balance of high cohesive strength and adhesion to low surface-energy substrates for lasting performance on squeezable containers. Specifically designed to exhibit excellent wetout characteristics and short-term removability. Meets the requirements of FDA 21 CFR 175.105 for indirect food contact. This section covers applications where incidental contact between food and adhesive could occur.

Type:	Emulsion acrylic
Minimum Application Temperature:	+23° F
Service Temperature Range:	-20° F to +200° F subject to facestock limitations



Let Us Label You

Typical Performance Data: 2 Mil Clear Polypropylene facestock at room temperature on standard lab panels.

HDPE

Loop Tack: 1.2 - 1.8 lbs
 Peel Adhesion: 1.1 - 1.7 lbs

PET

Loop Tack: 3.6 - 4.2 lbs
 Peel Adhesion: 2.6 - 3.2 lbs

Glass

Loop Tack: 2.6 - 3.2 lbs
 Peel Adhesion: 1.6 - 2.2 lbs

Liner:

Fasson® 40#BG is a bleached glassine white liner with excellent roll label converting properties. Designed for low- to medium-speed dispensing applications. Not recommended for sheeted applications. Features good back printability.

Basis Weight: 37.20# per ream
 (500 sheets 24" x 36")
 Caliper: 0.00211 inches ± 10%
 Tensile: MD 44 pounds per inch
 CD 19 pounds per inch
 Tear: MD 41 grams
 CD 46 grams

Total Construction Caliper (approximate): 0.00548 inches ± 10%

Optimal Storage Conditions

Unless otherwise specified in this document, ideally store at 72F and 50% RH

Statement of Practical Use

All materials, sales and contracts for sale of Avery Dennison products are sold with the express requirement and understanding that the customer is solely and exclusively responsible for testing and for ensuring the products are fit for the customer's purposes or an end-user's purposes. All express or implied warranties of merchantability and fitness for particular use are disclaimed.

Warranty

All sales and contracts for sale are expressly conditioned on the buyer's assent to Avery Dennison's terms and conditions found on its website at label.averydennison.com/products. Avery Dennison hereby objects to any term, different from or additional to Avery Dennison's terms, contained in any buyer communication in any form, unless agreed to in a writing signed by an officer of Avery Dennison.

label.averydennison.com

**Label and Packaging Materials-North America**

8080 Norton Parkway
 Mentor, OH 44060
 800-944-8511

