

Fasson® 3.7 Mil Smudgeproof Kimdura®/S4600/50#SCK**Spec# 79572****Facestock:**

3.7 Mil Smudgeproof Kimdura® is a white synthetic paper designed to be compatible with both thermal transfer and flexographic printing methods. It has good chemical resistance, tear strength, and cold temperature performance to -65° F. It is certified for Section 2 of BS 5609, and also certified for BS 5609, Section 3 with most suppliers' recommended ribbons for drum labeling.

Basis Weight:	n/a
Caliper:	0.0039 inches ± 10%
Tensile:	MD 11.90 lb/in CD 13.40 lb
Tear:	n/a
Stiffness:	n/a

Adhesive:

Fasson® S4600 is a clear general purpose permanent adhesive featuring good initial tack and ultimate adhesion to a wide variety of substrates. Meets the requirements of FDA 21 CFR 175.105 for indirect food contact.

Type:	Emulsion Acrylic
Minimum Application Temperature:	+10° F
Service Temperature Range:	-40° F to + 300° F subject to facestock limitations

1/25/2020

Typical Performance Data: 2 Mil Clear Polyester at room temperature on standard lab panels

Stainless Steel

Loop Tack: 2.77 lbs
Peel Adhesion: 4.1 lbs

Aluminum

Loop Tack: N/A
Peel Adhesion: 4.4 lbs

Alkyd Enamel Paint

Loop Tack: N/A
Peel Adhesion: 3.9 lbs

Polypropylene

Loop Tack: N/A
Peel Adhesion: 4.3 lbs

HDPE

Loop Tack: N/A
Peel Adhesion: 4.6 lbs

Liner:

Fasson® 50#SCK is a bleached super-calendered kraft stock featuring high internal strength, toughness, and tear resistance. Ideally suited for marginal punching, perforating, and fanfolding.

Basis Weight: 57.7# per ream \pm 10%
(500 sheets 24" x 36")
Caliper: 0.0032 inches \pm 10%
Tensile: MD 51.40# per inch width
CD 22.80# per inch width
Tear: MD 55.10 grams
CD 71.40 grams

Total Construction Caliper (approximate): 0.0079 inches \pm 10%

Optimal Storage Conditions

Unless otherwise specified in this document, ideally store at 72F and 50% RH

Statement of Practical Use

All materials, sales and contracts for sale of Avery Dennison products are sold with the express requirement and understanding that the customer is solely and exclusively responsible for testing and for ensuring the products are fit for the customer's purposes or an end-user's purposes. All express or implied warranties of merchantability and fitness for particular use are disclaimed.

Warranty

All sales and contracts for sale are expressly conditioned on the buyer's assent to Avery Dennison's terms and conditions found on its website at label.averydennison.com/products. Avery Dennison hereby objects to any term, different from or additional to Avery Dennison's terms, contained in any buyer communication in any form, unless agreed to in a writing signed by an officer of Avery Dennison.

label.averydennison.com



Label and Packaging Materials-North America

8080 Norton Parkway
Mentor, OH 44060
800-944-8511

10001372 QM15



ISO 9001:2015